

# LD5980M

## Thin Ultra Tack Film

### Description

LD5980G (Ultra tack sheet) is a white opaque thin calendered PVC film. It's designed for solvent inkjet printing. This is designed to meet high resolution printing with excellent color.

### Features

- Excellent printing performance
- Excellent weather resistance : Solvent based acrylic adhesive (Permanent Type)
- Release liner: Super flat, double side PE coated paper
- High performance aggressive permanent pressure sensitive adhesion

### Application

- Solvent inkjet & latex printing: Vutek, Arizona, Mimaki, Mutoh, Roland, DGI, HP etc.
- Selected smooth to rough wall surface
- Application : Smooth concrete, brick-type wall, patterned tile, Etc  
(Smooth means that texture of substrate is like fine sand paper, litter or no surface variation)

### Characteristics

Item	Description
Film	50 $\mu$ m opaque film
Thickness	95 $\mu$ m.with adhesive ( $\pm$ 10%)
Adhesive	Acrylic based pressure sensitive(Solvent based)
Adhesive color	Clear
Liner	Double sides PE coated paper(140g/m <sup>2</sup> )
Application surfaces	Flat
Application temp.	$\geq$ 10 $^{\circ}$ C (18 to 25 $^{\circ}$ C optimum)

### Durability

Durability is based on field experience and exposure tests in South Korea. Outdoor durability is 1 years when properly processed and applied (unprinted film vertical exposure).

### Expected Performance Life

Application Surface	Surface Texture	Warranty
Unpainted Concrete	Smooth(fine sand grain)	1 Year

## LG Hausys Sign & graphic materials

	Rough	3~6 Month
Unpainted Cement	Smooth(fine sand grain)	1 Year
	Rough	3~6 Month
Tile	Smooth	1 Year
	Patterned tile	6 Month
Painted Surface	Smooth	1 Year
	Rough	6 Month
Marble	Smooth	1 Year
	Rough	6 Month
Metal Surface	Smooth	1 Year

### \* Legend

- 1) Smooth: Flat and smooth surface allowing the entire surface to be in contact with film.
- 2) Rough: Uneven and corrugated surface or embossed surface which keeps parts of the surface from being in contact with film. Requires extra attention to lay down the film to the surface. The deepest crevices in the surface must be less than 1/8" deep for the film to work properly.

### *The Performance Life is influenced by*

- Installation technique : Improper installation techniques may cause edge curling, lifting & poor adhesion.
- Adhesion for outdoor graphics : The film is not to be durable in outdoor application if it is easily removed from the applied surface.( Customer must check the adhesion level before applying the graphics)
- Outdoor Graphics exposed to water from rain. Water can be trapped behind graphics applied outdoors, Leading to lifting of images
- The deepest crevices in the surface must be less than 1/8" deep for the film to be worked properly.
- Freezing & thawing cycles : If the graphic is applied to the outdoor walls ( which mean it is exposed To outdoor cycles of freezing & thawing), Moisture can be trapped between the wall and the graphics which result in graphics lifting as well as in spalling both within the wall and on the outdoor facing wall

In conclusion, The Performance Life Generally accords with the table above. But Installation environment, Different Applied surfaces, Severe Freezing & thawing cycles could shorten the warranty period of product.

### Application Guide

① Before application, carefully consider the surface area to determine whether the Ultra Tack adhesive is adequate for application. One needs to consider the initial tack required, possible damage to application surface upon removal of the film, and the duration of application. Unsound substrate, paint surface and textured wall paper may be damaged upon graphic removal.

Always test the film on the target surface for adhesion and adhesive transfer before undertaking a job. If the film is to be exposed to snow or rain, make sure that the edges are sealed as the adhesion / bond may weaken. If applying to a painted surface, the paint must be steady on the surface (not peel off when scratched).

## LG Hausys Sign & graphic materials

② Application surface must be cleaned one day prior to application and wiped for dust once more just before application. In case of rough surfaces, the crevices must also be cleaned out, then vacuumed clean. The surface must be completely dried before application.

③ Apply the film using a felt-tip squeegee or linen. When applying to a rough surface, also use a roller and a heat gun, applying at a steady speed of 2” per second. Eliminate any bubbles that may form during application.

### Removing Guide

① Permanent adhesive is not designed to be removed. It can be removed, but with great difficulty. Also, It can damage to the substrate. Even though it is removed, it may leave more than 50% adhesive residue. Some substrates are not allowed to have graphic removed.(unpainted wallboard, some flexible materials, special coating product such as anti-reflection and scratch resistance) In that case, film removal may damage substrate. IF application surface is concrete which is not thoroughly cleaned or has defects(like cracks or crevices), the dust or sand which remains application surface can be detached from the surface when removing the film.

② Film becomes brittle in cold weather(Under 10°C). Brittleness causes the film to break into small pieces during removal. Always keep the Removing temperature above 10°C. Generally, the higher temperature makes the job more easier.

③ Graphics that are applied to newly painted substrates – which means the painted area has not enough time to cure – make removal difficult. Painted surface must be thoroughly dried and cured with in accordance with paint manufacturer’s recommendations. Uncured and unsound painted substrate may be damaged by removing the Ultra Tack adhesive.

④ Heating a graphic- Using heat sources like heat gun – eases removal of the film. Heat softens the adhesive, reducing the pull-off force needed. Raise the graphic temperature to 70~80°C. Be sure not to burn or damage the film /the substrate by using excessive heat.

④ Using mild solvents (like IPA) or adhesive removal product can be used to get rid of adhesive residue. Some chemicals, however, may damage the substrate or its finish. Always test the chemical in a small, inconspicuous area, allowing the chemical to remain on the residue for the recommended time. Remove the residue and check for substrate damage. Below are the steps for Removing residues.

1. Test specific solvents or remover (Below is “remover”) by applying it in inconspicuous area to confirm that it is adequate for the substrate.
2. Allow the remover to penetrate the adhesive in the prescribed time.
3. Remove softened adhesive by scraping with a rivet brush.
4. Pick up the loosened adhesive with a cloth wetted with remover.

## LG Hausys Sign & graphic materials

5. Repeat steps 2~4 as needed
6. After the residue is fully removed, clean the entire surface.
7. To keep the substrate more cleanly, wash it with a solution of detergent and water.

### Shelf Life

Shelf life is 1 year from factory shipment.

Storage condition: Free from excessive moisture, temperature, direct sunlight (20°C x 50% R.H)

### Physical Properties

Property	Specification	Test Method
Thickness (Including adhesive)	95 $\mu$ m $\pm$ 10%	Micrometer
Tensile strength	$\geq$ 1.4kg/cm	ASTM 882
Elongation	$\geq$ 100%	ASTM 882
Peel adhesion(24hrs)	$\geq$ 2,000g/in	180 peeling PSTC-1
Service temp. range	-25°C ~ 82°C	Film applied Al panels 24hrs prior test
Application temp.	$\geq$ 10°C	18 to 25°C optimum, on clean substrate
Opacity	Tt $\leq$ 20	Haze Meter (Tt: Transmission)
Gloss	50 $\uparrow$	@60, in Machine Direction
Dimensional Stability	Max 1.2mm	Adhered to Aluminum Plate, Length Direction (80°C Oven, 24hr , Average)
Release liner thickness/weight	0.15mm $\pm$ 10%/140g/m <sup>2</sup>	Micrometer

#### Notice :

*The information provided on this sheet represents typical properties and does not constitute a specification. No liability will be accepted for errors and omissions and in no circumstances shall LG Chem Ltd be liable for any loss or injury arising directly or as a consequence of the publication of this data sheet. All LG Chem vinyl sold subject to our conditions of sale. LG Chem also retains the right to change sizes and specifications of products without prior notice.*