

ORAGUARD® 297GF OPTICALLY CLEAR PREMIUM CAST PVC LAMINATING FILM

Technical Datasheet
07/14
Page 1 of 1

Description

2.75-mil, premium optically clear cast PVC film with a UV extension factor of four years. Available in gloss finish.

Release Liner

1.6-mil silicone-coated polyester film

Adhesive

Clear, solvent-based, permanent adhesive

Applications

Especially developed for protection of the printed ORAJET® Window-Graphics films. The laminating film with its optimized hardness covers the perforated film so that no humidity, dust or other contaminations can penetrate the perforation of the film.

Technical Data

Thickness (without liner and adhesive)	2.75-mil
Temperature Resistance	Adhered to aluminum, -58°F to +230°F, no variation
Fire Behavior (DIN 75200)	Adhered to steel, self-extinguishing
Fire Rating	ASTM E 84-07 Class "A"
Adhesive Power (FINAT TM-1, after 24 h, average)	Adhered to stainless steel: 2.74 lb/in
Tensile Strength (DIN EN ISO 527)	Along: Min. 19 MPa Across: Min. 19 MPa
Elongation at Break (DIN EN ISO 527)	Along: Min. 120% Across: Min. 120%
Seawaterability (DIN 50 021)	Adhered to aluminum, after 100h/73°F, no variation
Shelf Life (68°F/50% relative humidity)	2 years
Minimum Life Expectancy (based on accepted application procedures on vertical surfaces)	8 years
Minimum Application Temperature	46°F
Available Lengths	150' (50-yard), 30' (10-yard)
Available Widths	24", 30", 54"
Recommended to be used in combination with	ORAJET® Series 3850, 3676, 3675, 3551, 3551RA, 3551DT
UV Protection Extension Factor	+4 years

For best results, utilize ORAFOL ICC profiles available at www.orafolamericas.com and allow solvent-based inks to dry for at least 24 hours (48-72 hours preferred) at 70°F before cutting the graphic to the ink or applying a laminate.

Note

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be completely cured. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Films with structured surface are naturally more sensitive than the unstructured. Accordingly, these films are to be treated carefully both in processing and in cleaning. Impurities affect the appearance of structured films and require more frequent cleaning. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

IMPORTANT NOTICE

All ORAGUARD® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORAGUARD® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORAGUARD® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use.

All specifications are subject to change without prior notice.



ORAFOL Americas – GA
1100 Oracal Parkway
Black Creek, GA 31308
Phone: 888.672.2251

ORAFOL Americas – CT
120 Darling Drive
Avon, CT 06001
Phone: 800.654.7570

ORAFOL Canada
2831 Bristol Circle
Oakville, Ontario L6H 6X5
Phone: 888.727.3374

techsupport-americas@orafol.com – www.orafolamericas.com