

DATA SHEET for:

Knitted Poly Satin FR

Product Code: FKPP3
Available Widths (m): 1.03, 1.53, 1.83 and 3.06
Roll Lengths (m): 50, 100 supplied on a 76mm (3") full width core

PROPERTY	TEST METHOD	RESULT
Fire Retardancy	BS5867	Type B
Fire Retardancy	DIN4102	B1
Yarn Composition	Not tested	100% Bright Polyester
Weight	BS2471	135gsm
Bursting Strength	ISO13938 - 2	>600Kpa

Information and test results for guidance only and may change without prior notice, Customer to determine suitability of product for the intended end use. V3

Suitable for dye-sublimation and digital printing with solvent, eco-solvent and UV inks **Knitted Poly Satin** is a high performance knitted polyester fabric that gives excellent colour reproduction and a luxurious appearance.

Treatments available: pure, digital pre-treatments for solvent, eco-solvent, UV, aqueous or disperse inks and flame retardant options comply with FR standards above

Colour: optic white to optimise print performance.

Typical end uses: internal and external banners, soft signage, retail display graphics, pop ups, display systems and promotional advertising applications





Report on the trial results of the fire-tunnel tests according to DIN 4102-1

Test-Nr.	01.52.4380.07	Date: 17 th April, 2007
Applicant	Brook International, Riparian Way, Cross Hills, Keighley, West Yorkshire BD20 7BW	
Material tested	Fabric	
Material name	Knitted Poly Satin FKPD3 Brook Digital 7	

Material data

Test thickness	mm	Climatised storage	yes
Average surface area mass	g/m ²	Preliminary end of test	no
Average raw density	kg/m ³	No. of tests required for main examination	
Glow remains according to DIN 52330	%	Miscellaneous details:	

Test units		A	B	C	D
First flames *)	min, sec	0:03			
Max. flame height	cm	40			
Point of time *)	min, sec	0:25			
Melting point *)	min, sec	0:03			
Flames on reverse side of test unit *)	min, sec	-			
Influence on burner flame *)	min, sec	0:11			
Burning components drip down *)	min, sec	0:07			
Extent		moderate			
Continuation of burning on the perforated bottom **)	min, sec	-			
Max. smoke temperature	°C	112			
Appeared after *)	min, sec	10:00			
Smoke density		low			
Glowing particles after test end **)	min, sec	-			
Remaining lengths	Test 1	cm	61		
	Test 2	cm	64		
	Test 3	cm	58		
	Test 4	cm	61		
Average value of single test		cm	61		

Remarks:---

The test material passed the „Brandschacht“ to DIN 4102-B1.

[Signature]
ppa. Dr. Kanig

[Signature]
i. A. Maßmann

*) Point of time referred to the test beginning
**) Time period

Art der Anforderung	Anforderungen		
	A 1	A 2	B 1
Brandschacht			
- Restlänge			
a) Mittelwert jedes Schachtes	> 35 cm	> 35 cm	> 15 cm
b) Einzelwerte	> 20 cm	> 20 cm	> 0 cm
- Rauchgastemperatur	< 125 °C	< 125 °C	< 200 °C
- Entflammung auf der Probenrückseite	nein	nein	zulässig
- Brandparallelscheinungen	kein Anlass zu Bedenken		
- weitere Nachweise	750°C Ofen, Rauchdichte, Toxizität, ggf. Heizwert		B2-Brennkasten

This information sheet is not a certificate of building material class according to DIN 4102-1.

quick - mix Gruppe GmbH & Co. KG

Mühlenschweg 7 ♦ 49090 Osnabrück ♦ Tel. +49 5 41 6 01-01 ♦ Fax 6 01-769





Report on the trial results of the fire-tunnel tests according to DIN 4102-1

Test-Nr.	01.52.4329.07	Date:	6 th February, 2007
Applicant	Brook International, Riparian Way, Cross Hills, Keighley, West Yorkshire BD20 7BW		
Material tested	Fabric		
Material name	FKPP3 KW01 Satin Optic White FR		


Material data


Test thickness	mm	Climatised storage	yes
Average surface area mass	g/m ²	Preliminary end of test	no
Average raw density	kg/m ³	No. of tests required for main examination	
Glow remains according to DIN 52330	%	Miscellaneous details:	

Test units		A	B	C	D
First flames *)	min, sec	0:03			
Max. flame height	cm	40			
Point of time *)	min, sec	0:25			
Melting point *)	min, sec	0:03			
Flames on reverse side of test unit *)	min, sec	-			
Influence on burner flame *)	min, sec	-			
Burning components drip down *)	min, sec	0:06			
Extent		moderate			
Continuation of burning on the perforated bottom **)	min, sec	-			
Max. smoke temperature	°C	115			
Appeared after *)	min, sec	10:00			
Smoke density		low			
Glowing particles after test end **)	min, sec	-			
Remaining lengths	Test 1	cm	61		
	Test 2	cm	63		
	Test 3	cm	63		
	Test 4	cm	59		
Average value of single test		cm	62		

Remarks:

The test material passed the „Brandschacht“ to DIN 4102-B1.


ppa. Dr. Kanig


i. A. Maßmann

*) Point of time referred to the test beginning
**) Time period

Art der Anforderung	Anforderungen		
	A 1	A 2	B 1
Brandschacht			
- Restlänge			
a) Mittelwert jedes Schachtes	> 35 cm	> 35 cm	> 15 cm
b) Einzelwerte	> 20 cm	> 20 cm	> 0 cm
- Rauchgastemperatur	< 125 °C	< 125 °C	< 200 °C
- Entflammung auf der Probenrückseite	nein	nein	zulässig
- Brandparallelerscheinungen	kein Anlass zu Bedenken		
- weitere Nachweise	750°C Ofen, Rauchdichte, Toxizität, ggf. Heizwert	B2-Brennkasten	

This information sheet is not a certificate of building material class according to DIN 4102-1.

quick - mix Gruppe GmbH & Co. KG

Mühlenschweg 7 ♦ 49090 Osnabrück ♦ Tel. +49 5 41 6 01-01 ♦ Fax 6 01-769



TFT

(Ilkley) Ltd.

The Sidings Business Park, SKIPTON, North Yorkshire, BD23 1TB
Phone or Fax 01756 792525

Office: 30 Alexandra Crescent, ILKLEY, West Yorkshire, LS29 9ER. Phone or Fax 01943 603459

Reg. No. 3168606, VAT No. 659 9604 77



TEST CERTIFICATE

No. F08038/3

Assessment to BS 5867 : 1980 Specification for Fabrics for
Curtains and Drapes, Part 2 : Flammability Requirements using BS 5438 : 1976

SAMPLE INFORMATION

Client **Brook International, Flagship House, Riparian Way, Cross Hills, KEIGHLEY, BD20 7BW**
Fabric Reference **Knitted Poly Satin FR FKPP3.**
Dimensions **50cm by 153cm**
Date Received **04.02.08**
Pre-treatment **None.**
Conditioning **BS 5438 : 1976, Clause 4.**

TESTING

Following the pre-treatment described above, the material was conditioned and tested according to **Test 2 of BS 5438 : 1976 Method of test for flammability of vertically oriented textile fabrics and fabric assemblies subjected to a small igniting flame**, using a **15 second flame application time** and the results assessed according to the requirements of **BS 5867 : 1980 Specification for Fabrics for Curtains and Drapes, Part 2 : Flammability Requirements**. Testing was carried out on the face side of the fabric.

Specimen No.	WARP			WEFT		
	1	2	3	1	2	3
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming debris separated	No	No	No	No	No	No

It should be noted that the results may not apply to situations where there is a restricted air supply or prolonged exposure to intense heat as in a conflagration.

CONCLUSION

The sample, as received, meets BS 5867 : 1980 Specification for Fabrics for Curtains and Drapes, Part 2, Flammability Requirements, Type B.

It should be noted that the fabric should be supplied with the manufacturers name, trademark or other identifying mark; the statement 'Flammability complies with the requirements of BS 5867 : Part 2, Type B' and instructions on any special precautions to be taken concerning care (including cleansing) of the product to be manufactured from the fabric, preferably using an appropriate care labelling symbol in accordance with BS 2747 and taking account of the pre-treatment used in this test and the requirements of Clause 4 of BS 5867 : Part 2 : 1980. Since the fabric is FR treated it should indicate "IF WETTED IN ANY WAY IT IS ESSENTIAL TO RE-TREAT THE FABRIC TO MEET FLAMMABILITY REQUIREMENTS".

Mr J Firth
Technical Manager

END OF REPORT