

**DATA SHEET for:**

**Brook Sailcloth FR**

**Product Code:** SAIL  
**Available Widths (m):** 1.60, and 3.20  
**Roll Lengths (m):** 50 supplied on a 76mm (3") full width core

PROPERTY	TEST METHOD	RESULT
Fire Retardancy	BS5867	Type B
Yarn Composition	Not tested	100% Semi dull Polyester
Weight	BS2471	170gsm
Tensile Strength	BS EN ISO13934	2.5N x 1.5N

Information and test results for guidance only and may change without prior notice, Customer to determine suitability of product for the intended end use. V3

Suitable for dye-sublimation and digital printing with solvent, eco-solvent and UV inks **Sailcloth FR** is a woven high tenacity polyester fabric with a dense construction to give excellent light dissipation and colour reproduction.

**Treatments available:** digital flame retardant polyurethane pre-treatment for solvent, eco-solvent, UV and dye-sublimation

**Colour:** optic white to optimise print performance

**Typical end uses:** internal and external banners, illuminated light boxes, soft signage, retail display graphics, hanging banners, murals, museum graphics, display systems, promotional advertising, advertising and promotional tents and marquees for corporate events



# TFT

(Ilkley) Ltd.

The Sidings Business Park, SKIPTON, North Yorkshire, BD23 1TB  
Phone or Fax 01756 792525

Office: 30 Alexandra Crescent, ILKLEY, West Yorkshire, LS29 9ER, Phone or Fax 01943 603459

Reg. No. 3168606, VAT No. 659 9604 77



## TEST CERTIFICATE

No. 06774/8

Assessment to BS 5867 : 1980 Specification for Fabrics for  
Curtains and Drapes, Part 2 : Flammability Requirements using BS 5438 : 1976

### SAMPLE INFORMATION

Client Brook International, Flagship House, Riparian Way, Cross Hills, KEIGHLEY,  
BD20 7BW  
Fabric Reference WSAIL Sailcloth FR 100% Polyester, Batch No. 3702.  
Dimensions 54cm by 150cm (Full width)  
Date Received 14.12.06  
Pre-treatment None.  
Conditioning BS 5438 : 1976, Clause 4.

### TESTING

Following the pre-treatment described above, the material was conditioned and tested according to **Test 2 of BS 5438 : 1976 Method of test for flammability of vertically oriented textile fabrics and fabric assemblies subjected to a small igniting flame**, using a **15 second flame application time** and the results assessed according to the requirements of **BS 5867 : 1980 Specification for Fabrics for Curtains and Drapes, Part 2 : Flammability Requirements**. Testing was carried out on the face side of the fabric.

Specimen No.	WARP			WEFT		
	1	2	3	1	2	3
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming debris separated	No	No	No	No	No	No

It should be noted that the results may not apply to situations where there is a restricted air supply or prolonged exposure to intense heat as in a conflagration.

### CONCLUSION

The sample, as received, meets **BS 5867 : 1980 Specification for Fabrics for Curtains and Drapes, Part 2, Flammability Requirements, Type B**.

It should be noted that the fabric should be supplied with the manufacturers name, trademark or other identifying mark; the statement 'Flammability complies with the requirements of BS 5867 : Part 2, Type B' and instructions on any special precautions to be taken concerning care (including cleansing) of the product to be manufactured from the fabric, preferably using an appropriate care labelling symbol in accordance with BS 2747 and taking account of the pre-treatment used in this test and the requirements of Clause 4 of BS 5867 : Part 2 : 1980.

Mr J Leadbeater LL.B DTS  
Technical Manager  
END OF REPORT